

AMENDMENTS TO THE CLAIMS

Listing of the claims:

Following is a listing of all claims in the present application, which listing supersedes all previously presented claims:

1. (Currently Amended) A membrane-electrode structure comprising:

an anode electrode₁;

a cathode electrode₂; and

a polymer electrolyte membrane made of a sulfonated polyarylene based polymer and held between both electrodes, wherein₁[[:]]

said cathode electrode comprises an electrode catalyst layer containing a catalyst particle having the catalyst loaded on the carbon particles, a pore forming member and an ion conducting polymer that is in contact with said polymer electrolyte membrane through said electrode catalyst layer, a ratio of the weight of the ion conducting polymer to the weight of the carbon particles ~~ratio~~ falling within the range of from 1.0 1.4 to 1.8 in relation to said carbon particles, and is in contact with said polymer electrolyte membrane through said electrode catalyst layer₁[[:]]and

said electrode catalyst layer having pores formed therein by the pore forming member, and has a total sum volume of the pores that have a ~~falling within the~~ pore diameter within a range of from 0.01 to 30 μm is equal to or greater, ~~of pores formed by said pore-forming member, equal to or more than~~ 6.0 $\mu\text{l}/\text{cm}^2$ mg catalyst.

2. (Original) The membrane-electrode structure according to claim 1, wherein the pores formed by said pore forming member have a pore diameter

distribution comprising a first peak falling within the pore diameter range from 0.01 to 0.1 μm and a second peak falling within the pore diameter range from 0.1 to 1.0 μm .

3. (Withdrawn) A polymer electrolyte fuel cell in which in the membrane-electrode structure comprising:

an anode electrode[[]];

a cathode electrode; and

a polymer electrolyte membrane made of a sulfonated polyarylene based polymer and held between both electrodes, wherein

a fuel gas is supplied to said anode electrode, an oxidant gas less than 50% in relative humidity is supplied to said cathode electrode and electric power is thereby generated under a low humidified condition, and wherein:

said cathode electrode comprises an electrode catalyst layer containing a catalyst particle having the catalyst loaded on the carbon particles, a pore forming member and an ion conducting polymer that is in contact with said polymer electrolyte membrane through said electrode catalyst layer, a ratio of the weight of the ion conducting polymer to the weight of the carbon particles ~~ratio~~ falling within the range of from 1.0 1.4 to 1.8 ~~in relation to said carbon particles, and is in contact with said polymer electrolyte membrane through said electrode catalyst layer;~~

said electrode catalyst layer having pores formed therein by the pore forming member, and ~~has~~ a total sum volume of the pores that have a ~~falling within the~~ pore diameter within a range of ~~falling within the pore diameter range~~ from 0.01 to 30

μm is ~~, of the pores formed by said pore forming member,~~ equal to or greater ~~more~~ than $6.0 \mu\text{l}/\text{cm}^2$ mg catalyst; and

the pores formed by said pore forming member have a pore diameter distribution comprising a first peak falling within the pore diameter range of from 0.01 to $0.1 \mu\text{m}$ and a second peak falling within the pore diameter range of from 0.1 to $1.0 \mu\text{m}$, the height of said first peak being higher than the height of said second peak.

4. (Withdrawn) The polymer electrolyte fuel cell according to claim 3, wherein the ion conducting polymer contained in the electrode catalyst layer of said cathode electrode has a weight ratio falling within the range of from 1.2 to 1.8 in relation to said carbon particles.

5. (Withdrawn) The polymer electrolyte fuel cell according to claim 3, wherein the electrode catalyst layer of said cathode electrode is bonded by thermal transfer to said polymer electrolyte membrane, and the pore diameter distribution of the pores formed by said pore forming member in said electrode catalyst layer, before thermal transfer, comprises a third peak in the pore diameter range equal to or more than $5 \mu\text{m}$, and wherein the height of said third peak falls within the range from 0.9 to $1.8 \mu\text{l}/\text{cm}^2$ mg catalyst in terms of the pore volume.

6. (Withdrawn) An electric appliance wherein a polymer electrolyte fuel cell is used in which:

in the membrane-electrode structure comprising an anode electrode, a cathode electrode and a polymer electrolyte membrane made of a sulfonated polyarylene based polymer and held between both electrodes, a fuel gas is supplied to said anode electrode, an oxidant gas less than 50% in relative humidity is supplied to said cathode electrode and electric power is thereby generated under a low humidified condition, said cathode electrode comprises an electrode catalyst layer containing a catalyst particle having the catalyst loaded on the carbon particles, a pore forming member and an ion conducting polymer of the weight ratio falling within the range from 1.0 to 1.8 in relation to said carbon particles, and is in contact with said polymer electrolyte membrane through said electrode catalyst layer;

said electrode catalyst layer has a total sum volume of the pores falling within the pore diameter range from 0.01 to 30 μm , of the pores formed by said pore forming member, equal to or more than 6.0 $\mu\text{l}/\text{cm}^2\text{mg}$ catalyst; and

the pores formed by said pore forming member have a pore diameter distribution comprising a first peak falling within the pore diameter range from 0.01 to 0.1 μm and a second peak falling within the pore diameter range from 0.1 to 1.0 μm , the height of said first peak being higher than the height of said second peak.

7. (Withdrawn) A transport machine wherein a polymer electrolyte fuel cell is used in which:

in the membrane-electrode structure comprising an anode electrode, a cathode electrode and a polymer electrolyte membrane made of a sulfonated polyarylene based polymer and held between both electrodes, a fuel gas is supplied to said anode

electrode, an oxidant gas less than 50% in relative humidity is supplied to said cathode electrode and electric power is thereby generated under a low humidified condition, said cathode electrode comprises an electrode catalyst layer containing a catalyst particle having the catalyst loaded on the carbon particles, a pore forming member and an ion conducting polymer of the weight ratio falling within the range from 1.0 to 1.8 in relation to said carbon particles, and is in contact with said polymer electrolyte membrane through said electrode catalyst layer;

said electrode catalyst layer has a total sum volume of the pores falling within the pore diameter range from 0.01 to 30 μm , of the pores formed by said pore forming member, equal to or more than 6.0 $\mu\text{l}/\text{cm}^2$ mg catalyst; and

the pores formed by said pore forming member have a pore diameter distribution comprising a first peak falling within the pore diameter range from 0.01 to 0.1 μm and a second peak falling within the pore diameter range from 0.1 to 1.0 μm , the height of said first peak being higher than the height of said second peak.

8. (Currently Amended) A polymer electrolyte fuel cell having ~~in which in the~~
a membrane-electrode structure comprising:

an anode electrode;[[,]]

a cathode electrode; and

a polymer electrolyte membrane made of a sulfonated polyarylene based polymer and held between both electrodes, wherein

a fuel gas is supplied to said anode electrode, an oxidant gas of 50% or more in relative humidity is supplied to said cathode electrode and electric power is thereby generated under a highly humidified condition, and wherein[[:]]

said cathode electrode comprises an electrode catalyst layer containing a catalyst particle having the catalyst loaded on ~~the~~ carbon particles, a pore forming member and an ion conducting polymer that is in contact with said polymer electrolyte membrane through said electrode catalyst layer, a ratio of the weight of the ion conducting polymer to the weight of the carbon particles ~~ratio~~ falling within the range of from 1.4 to 1.8 in relation to said carbon particles, and is in contact with said polymer electrolyte membrane through said electrode catalyst layer;

said electrode catalyst layer having pores formed therein by the pore forming member, and has a total sum volume of the pores that have a ~~falling within the pore diameter~~ within a range of from 0.01 to 30 μm is equal to or greater, ~~of the pores formed by said pore forming member, equal to or more than 6.0 $\mu\text{l}/\text{cm}^2$ mg catalyst; and~~

the pores formed by said pore forming member have a pore diameter distribution comprising a first peak falling within the pore diameter range of from 0.01 to 0.1 μm and a second peak falling within the pore diameter range of from 0.1 to 1.0 μm , the height of said first peak being lower than the height of said second peak.

9. (Currently Amended) The polymer electrolyte fuel cell according to claim 8, wherein the ion conducting polymer contained in the electrode catalyst layer of said cathode electrode falls within the weight ratio range of from ~~1.4~~ 1.4 to 1.6 in relation to said carbon particles.

10. (Original) The polymer electrolyte fuel cell according to claim 8, wherein the electrode catalyst layer of said cathode electrode is bonded by thermal transfer to said polymer electrolyte membrane, and the pore diameter distribution of the pores formed by said pore forming member in said electrode catalyst layer, before thermal transfer, comprises a third peak in the pore diameter range equal to or more than $5\text{ }\mu\text{m}$, and wherein the height of said third peak is $0.18\text{ }\mu\text{l/cm}^2\text{ mg catalyst}$ or more in terms of the pore volume.

11. (Currently Amended) An electric appliance utilizing ~~wherein~~ a polymer electrolyte fuel cell, the polymer electrolyte fuel cell comprising ~~is used in which:~~

a ~~in the~~ membrane-electrode structure comprising:

an anode electrode;[[.]]

a cathode electrode; and

a polymer electrolyte membrane made of a sulfonated polyarylene based polymer and held between both electrodes, wherein a fuel gas is supplied to said anode electrode, an oxidant gas of 50% or more in relative humidity is supplied to said cathode electrode and electric power is thereby generated under a highly humidified condition, and wherein:

said cathode electrode comprises an electrode catalyst layer containing a catalyst particle having the catalyst loaded on the carbon particles, a pore forming member and an ion conducting polymer that is in contact with said polymer electrolyte membrane through said electrode catalyst layer, a ratio of the weight of the ion conducting polymer to the weight of the carbon particles ~~ratio~~ falling within the range of

from ~~1.0~~ 1.4 to 1.8 in relation to said carbon particles, and is in contact with said polymer electrolyte membrane through said electrode catalyst layer;

said electrode catalyst layer having pores formed therein by the pore forming member, and has a total sum volume of the pores that have a falling within the pore diameter within a range of from 0.01 to 30 μm , is equal to or greater, of the pores formed by said pore forming member, equal to or more than 6.0 $\mu\text{l}/\text{cm}^2$ mg catalyst; and

the pores formed by said pore forming member have a pore diameter distribution comprising a first peak falling within the pore diameter range of from 0.01 to 0.1 μm and a second peak falling within the pore diameter range of from 0.1 to 1.0 μm , the height of said first peak being lower than the height of said second peak.

12. (Currently Amended) A transport machine utilizing ~~wherein~~ a polymer electrolyte fuel cell, the polymer electrolyte fuel cell comprising ~~is used in which: in the~~ a membrane-electrode structure comprising:

an anode electrode;[[,]]

a cathode electrode; and

a polymer electrolyte membrane made of a sulfonated polyarylene based polymer and held between both electrodes, wherein

a fuel gas is supplied to said anode electrode, an oxidant gas of 50% or more in relative humidity is supplied to said cathode electrode and electric power is thereby generated under a highly humidified condition, and wherein

said cathode electrode comprises an electrode catalyst layer containing a catalyst particle having the catalyst loaded on the carbon particles, a pore forming

member and an ion conducting polymer that is in contact with said polymer electrolyte membrane through said electrode catalyst layer, a ratio of the weight of the ion conducting polymer to the weight of the carbon particles ratio falling within the range of ~~from 1.0~~ 1.4 to 1.8 in relation to said carbon particles, and is in contact with said polymer electrolyte membrane through said electrode catalyst layer;

said electrode catalyst layer having pores formed therein by the pore forming member, and has a total sum volume of the pores that have a falling within the pore diameter within a range of from 0.01 to 30 μm is equal to or greater, ~~of pores formed by said pore forming member, equal to or more than~~ 6.0 $\mu\text{l}/\text{cm}^2$ mg catalyst; and

the pores formed by said pore forming member have a pore diameter distribution comprising a first peak falling within the pore diameter range from 0.01 to 0.1 μm a second peak falling within the pore diameter range from 0.1 to 1.0 μm , the height of said first peak being lower than the height of said second peak.